

# Shinn Thon UK Ltd

1<sup>st</sup> Floor, 223 Dalton Road, Barrow in Furness, Cumbria. LA14 1PQ  
Tel: 0870 609 2264 Fax: 01229 833 733 E-mail: sales@shinnthon.com

---

## Product Datasheet

# SH5005-MPK

PVC Insulation Tape FR 8M--Multipack



### Specifications:

PVC insulation tape 8M

Fire Retardant

Standard Colors: black/green/blue/red/white/yellow other colors available on request

Width: 19mm

Pack: 6MPK/10MPK/24MPK

#### SH5005-6MPK

One each of Black, Red, Yellow, Blue, Green and White

#### SH5005-10MPK

2 Yellow

2 Blue

2 Green

2 Red

2 White

#### SH5005-24MPK:

10 Black

2 Red

2 White

2 Yellow

2 Blue

2 Brown

2 Green

2 Green/Yellow

*Dimensions may differ from those shown*

# Shinn Thon UK Ltd

1<sup>st</sup> Floor, 223 Dalton Road, Barrow in Furness, Cumbria. LA14 1PQ  
Tel: 0870 609 2264 Fax: 01229 833 733 E-mail: sales@shinnthon.com

---

## Applications

- Colour coding and insulation of electrical cabling
- Masking off during chemical and electro-plating
- Degaussing and coil wrapping
- Colour coding components, intermediate stock and finished goods during manufacture
- Masking and protection of aircraft portholes during manufacture
- Cable harnessing, insulation, abrasion protection for OEM companies in household appliances market

## Technology Data:

Total thickness	Peel adhesive	Tensile Strength	Voltage Breakdown	Elongation	Fire Retardant	Service temperature range
(mm)	(N/CM)	(N/CM)	(Kv)	(%)	(s)	(°C)
0.13	≥1.6	≥22	7.5	≥180%	Pass( UL510)	-12°C -> +80°C

## Usage:

Temperature: between 0°C and + 50°C. Surface must be clean and free from dust and grease. Avoid touching the tapes exposed adhesive surface in order to keep full adhesive performance. Pressure sensitive adhesive must be applied with a maximum of pressure in order to achieve maximum pressure level. The indicated level of performance will be reached after a bonding period of 24 HRS at 23 °C.

## Storage and shelf life

Clean and dry in a well ventilated area, preferably at a temperature between 10°C and 30°C. Stored under these conditions shelf life will be a minimum of 6 months.

## Complies to:

RoHS 2011/65/EU

BS EN60454-2

Issue Date: 01/01/2013
Revision: E